TECHNICAL DATA

POLYURETHANE ADHESION PROMOTER

DESCRIPTION A one component, adhesion promoter for brush, roller or low pressure spray

application.

USES Polyurethane Adhesion Promoter is developed for use as an adhesion promoting

primer for glass and concrete substrates and other siliceous surfaces, especially highly polished surfaces, prior to coating with Uroxsys polymeric coatings.

FEATURES A one pack system with low odour during installation and excellent adhesion to glass

and cementitious substrates.

COLOUR Clear

SURFACE PREPARATION

ARATION Substrates need to be clean, dry and dust free. Light etching with Uroxsys CCA

followed by thorough washing with clean water may be required to remove polishing

residue from ground concrete.

CCA prior to using this adhesion promoter improves adhesion to ceramic tiles and

polymer modified concrete.

APPLICATION Apply in an even coat at 10-20 m², depending on substrate, per litre to wet the

surface. Do not flood or puddle. Use mohair rollers, wide brush or low pressure spray.

TECHNICAL DATA Composition: Organo-Silane solution in alcohol

Film Thickness: 5 microns per coat DFT Coverage Rate: 10-20 m² per litre

Touch Dry (Dust Free): Approximately 2 hours @ 20 □ C

Topcoating: Recoat within one day. Ensure good ventilation. Apply

polyurethane after 4 hours minimum cure.

Special Note: There must be enough time allowed to ensure that all the

alcohol solvents, as well as the alcohol generated by the primer's cure mechanism, are fully evaporated. Alcohols,

if present, can adversely affect the curing of

polyurethanes.

Flashpoint: 12°C

Shelf Life: 6 months in unopened container Clean Up: Warm water with detergent

SAFETY DATA If spraying wear a positive air-supplied full-face respirator. Avoid breathing the dust

when sanding, use a dust mask. Wear protective clothing and safety glasses. Gloves are essential. Avoid contact with exposed skin. Before commencing

work, apply barrier cream.

Contains ethanol, absorption via skin and breathing fumes will raise blood alcohol

level.

This information is, to the best of our knowledge, true and accurate, but any recommendations or suggestions which may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

2K PROMOTER TD5 JAN22