



## TECHNICAL DATA

### POLYURETHANE ADHESION PROMOTER

<b>DESCRIPTION</b>	A one component, adhesion promoter for brush, roller or low pressure spray application.																
<b>USES</b>	Polyurethane Adhesion Promoter is developed for use as an adhesion promoter primer for glass and concrete substrates, especially highly polished surfaces.																
<b>FEATURES</b>	A one pack system with low odour during installation and excellent adhesion to glass and cementitious substrates.																
<b>COLOUR</b>	Clear																
<b>SURFACE PREPARATION</b>	Substrates need to be clean, dry and dust free. Light etching with Uroxsys CCA may be required to remove polishing residue from ground concrete.																
<b>APPLICATION</b>	Apply in an even coat at 10-20 m <sup>2</sup> per litre to wet the surface. Do not flood or puddle. Use mohair rollers, wide brush or low pressure spray.																
<b>TECHNICAL DATA</b>	<table><tr><td>Composition:</td><td>Silane solution</td></tr><tr><td>Film Thickness:</td><td>5 microns per coat DFT</td></tr><tr><td>Coverage Rate:</td><td>10-20 m<sup>2</sup> per litre per coat</td></tr><tr><td>Touch Dry (Dust Free) :</td><td>Approximately 2 hours @ 20° C</td></tr><tr><td>Topcoating:</td><td>Recoat within one day. Ensure good ventilation. Apply polyurethane after 4 hours minimum cure.</td></tr><tr><td>Flashpoint:</td><td>12°C</td></tr><tr><td>Shelf Life:</td><td>6 months in unopened container</td></tr><tr><td>Clean Up:</td><td>Warm water with detergent</td></tr></table>	Composition:	Silane solution	Film Thickness:	5 microns per coat DFT	Coverage Rate:	10-20 m <sup>2</sup> per litre per coat	Touch Dry (Dust Free) :	Approximately 2 hours @ 20° C	Topcoating:	Recoat within one day. Ensure good ventilation. Apply polyurethane after 4 hours minimum cure.	Flashpoint:	12°C	Shelf Life:	6 months in unopened container	Clean Up:	Warm water with detergent
Composition:	Silane solution																
Film Thickness:	5 microns per coat DFT																
Coverage Rate:	10-20 m <sup>2</sup> per litre per coat																
Touch Dry (Dust Free) :	Approximately 2 hours @ 20° C																
Topcoating:	Recoat within one day. Ensure good ventilation. Apply polyurethane after 4 hours minimum cure.																
Flashpoint:	12°C																
Shelf Life:	6 months in unopened container																
Clean Up:	Warm water with detergent																
<b>SAFETY DATA:</b>	If spraying wear a positive air-supplied full-face respirator. Avoid breathing the dust when sanding, use a dust mask. Wear protective clothing and safety glasses. Gloves are essential. Avoid contact with exposed skin. Before commencing work, apply barrier cream.																

This information is, to the best of our knowledge, true and accurate, but any recommendations or suggestions which may be made are without guarantee, since the conditions of use are beyond our control. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

2K PROMOTER TD1/0504