



## MIXING INSTRUCTIONS

### DURACRETE SYSTEM SL AND SST COLOURED EPOXY TOPPING FOR BULK SUPPLIED FILLER, USING SYSTEM SL OR SST HARDENER.

The uncoloured binder mix is:

System SL Resin	5.00 kg
System SL Hardener	3.09 kg

The coloured binder mix is

System SL Resin	5.00 kg
System SL Hardener	3.24 kg
Pigment Paste	0.50 kg

Mix Pigment paste into resin if required, then add hardener and mix thoroughly.

Add	J61W (F04)	5.00 kg
and	100G Silica (F07)	7.00 kg

Mix in and place as a self-leveller. Deaerate and broadcast with J61W or selected aggregate for SST topping.

### SPECIAL NOTE:

When using System SL with pigment paste, prior to overcoating with an approved topcoat (Duracoat AUGF, AUSF, ESF-80 or MCL) the surface must be thoroughly cleaned with a suitable solvent blend. Refer to the Caution statement on the product data sheets.